

**TEST REPORT NO: 191819**

Date: 27 September 2023

**PIERRE FREY SAS  
47 RUE DES PETITS CHAMPS  
75001 PARIS  
FRANCE**


The following sample(s) was/were submitted and identified by/on behalf of the client as:

Retailer	Not Specified
Description of article	F2500 TEDDY MOHAIR FABRIC
Retailer style number	BEIGE
Retailer Standard Number	UNKNOWN
Order No./ Buyer	ADELINE JELAGO
Quality/Fibre Composition	UNKNOWN
Date Sample Received/Test Started:	22 September 2023

Tests	Pass	Fail	Remarks
BS 5852 Crib 5	X		
BS 5852 Ignition Source 0 & 1	X		

(please note our uncertainty of measurement has been taken into account when the above results were pass/failed)  
(Any statement of conformity made in this report unless otherwise stated in the test specification(s) is in line with SGS United Kingdom (Leicester) Decision rule LEI-GEN-PROC-012).

Signature



**M. Harrison Laboratory Manager**

For and on behalf of  
SGS United Kingdom Ltd

All samples are conditioned to ISO 139 where conditioning is required (unless otherwise stated)

This document is issued by the Company under its General Conditions of Service accessible at [www.sgs.com/terms\\_and\\_conditions.htm](http://www.sgs.com/terms_and_conditions.htm) and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law." Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only

Customer: **PIERRE FREY SAS** Test Report No: **191819**

## Test Results

### BS 5852: Part 1: 1979

*Methods of test for the ignitability by smokers' materials of upholstered composites for seating.*

#### Test Requested

The test specimen supplied is F2500 teddy mohair fabric and has been tested using ignition sources 0 and 1 using the following test method BS 5852: Part 1: 1979.

#### Fibre Identification

Stated Fibre Composition: Unknown

#### Pre – Treatment

At the customer's request the sample was subject to a water soak procedure as described in BS 5651: 1978 Clause 4.5 and then line dried.

#### Conditioning

The materials to be tested and cigarettes were conditioned immediately before the test for 72 hours in an indoor ambient condition and then for at least 16 hours in an atmosphere having a temperature of  $20 \pm 5^{\circ}\text{C}$  and a relative humidity of  $50 \pm 20\%$ .

#### Comments of Test Results

The test specimen meets the requirements of clause 9 from BS 5852: Part 1: 1979 using ignition source 0 and 1.

#### Results

'The following tests results relate only to the ignitability of the combination of materials under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials in use'

**Customer:** PIERRE FREY SAS **Test Report No:** 191819

**Test Results**

Two cigarettes are placed along the junction between the horizontal and vertical test pieces in accordance with Clause 9.2.2. No progressive smouldering or flaming is to be observed within 1 hour of placement of the cigarette (Clause 9.2.4).

The Cigarette Test		
	Cigarette 1	Cigarette 2
Clause 9.2.3 Evidence of Progressive Smouldering/ Flaming or Afterglow.	No	No
Cover Splitting	No	No
Clause 9.4 Any Internal Progressive Smouldering during the Final Examination	No	No
Test Result	Pass	Pass

A butane flame is applied at the junction between the horizontal and vertical test pieces for a period 20 ± 1 second in accordance with clause 9.3.2. No Flaming or Progressive Smouldering is to be observed after 2 minutes of the removal of the burner tube (Clause 9.3.4).

The Match Test		
	Match 1	Match 2
Clause 9.3.4 Evidence of Flaming/ Progressive Smouldering/ Afterglow or Smoking	No	No
Cover Splitting	No	No
Clause 9.4 Any Internal Progressive Smouldering during the Final Examination	No	No
Test Result	Pass	Pass

Smouldering Cigarette test and the match test were carried out over Non-Fire Retardant Polyurethane Foam Density of 20-22 Kg per m<sup>3</sup>. The face of the fabric was tested.

Measurement of uncertainty

Ignition source 0: +0sec/-60sec progressive smouldering  
 Ignition source 1: +0sec/-60sec smouldering +0sec/-2sec flaming

This document is issued by the Company under its General Conditions of Service accessible at [www.sgs.com/terms\\_and\\_conditions.htm](http://www.sgs.com/terms_and_conditions.htm) and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only

Customer: **PIERRE FREY SAS** Test Report No: **191819**

### Test Results

#### BS 5852: 2006

#### Clause 11 using Ignition Source 5

#### Methods of test for assessment of the ignitability of upholstered seating by smouldering and flaming ignition sources

**Description of Test Sample: F2500 teddy mohair fabric**

#### Test Request

The sample supplied has been tested against the test method BS 5852: 2006 Clause 11 using ignition source 5.

#### Pre - Treatment

The customer has stated that the supplied test specimen has not been chemically treated so therefore no water soaking procedure has been performed.

#### Conditioning

The materials and cribs were conditioned for at least 72 hours in an indoor ambient temperature and then immediately before the test 24 hours in an atmosphere of  $23 \pm 2^\circ\text{C}$  and  $50 \pm 5\%$  r.h.

#### Comments on Test Results

The sample supplied meets the requirements of BS 5852: 2006 Clause 11, using ignition source 5.

#### Test Results

"The following test results relate only to the ignitability of the combination of upholstery composites (BS 5852:2006, Clause 11) under the particular conditions of test stated; they are not intended as a means of assessing the full potential fire hazard of the materials or products in use"

#### Uncertainty of Measurement

Smouldering: +0/-60secs  
Flaming: +0/-10secs

This document is issued by the Company under its General Conditions of Service accessible at [www.sgs.com/terms\\_and\\_conditions.htm](http://www.sgs.com/terms_and_conditions.htm) and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law." Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only

Customer: **PIERRE FREY SAS** Test Report No: **191819**

**Test Results**

	Criteria of Ignition	Test 1 Criteria Observed	Test 2 Criteria Observed
<b>Progressive smouldering ignition</b>	Clause 4.1.1 a	No	No
	Clause 4.1.1 c	No	No
	Clause 4.1.1 e	No	No
	Clause 4.1.1 f	No	No
<b>Flaming Ignition</b>	Clause 4.2.1 a	No	No
	Clause 4.2.1 b	No	No
	Clause 4.2.1 c	No	No
	Clause 4.2.1 e	No	No
	Clause 4.2.1 g	No	No
<b>Ignition occurring</b>		Non – Ignition	Non – Ignition

The test specimen was tested over Combustion modified foam (CMHR) with a density of 35kg/m<sup>3</sup>.

**Criteria of ignition**  
**Smouldering Ignition**

- Clause 4.1.1 (a) Test specimen displays escalating smouldering combustion behaviour so that it is unsafe to continue and requires forcible extinction.
- Clause 4.1.1 (c) Test specimen smoulders until it is essentially consumed or smoulders to the extremities.
- Clause 4.1.1 (e) Test specimen produces externally detectable amounts of smoke, heat or glowing 60 min after ignition of the crib.
- Clause 4.1.1 (f) Test specimen shows evidence of charring within the filling more than 100 mm in any direction apart from upwards.

**Flaming Ignition**

- Clause 4.2.1 (a) Test specimen displays escalating flaming combustion behaviour and requires forcible extinction.
- Clause 4.2.1 (b) Test specimen that burns until it is essentially consumed within the test duration.
- Clause 4.2.1 (c) Test specimen on which any flame front reaches the extremities of the test specimen other than the top of the vertical part, or passes through the full thickness of the specimen within the test duration.
- Clause 4.2.1 (e) Test specimen continues to flame for more than 10 minutes.
- Clause 4.2.1 (g) Test specimen from which flaming debris causes an isolated floor fire that continues to flame for longer than 10 minutes.

This document is issued by the Company under its General Conditions of Service accessible at [www.sgs.com/terms\\_and\\_conditions.htm](http://www.sgs.com/terms_and_conditions.htm) and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only

Customer:

PIERRE FREY SAS

Test Report No:

191819

## Test Results



End of Report

This document is issued by the Company under its General Conditions of Service accessible at [www.sgs.com/terms\\_and\\_conditions.htm](http://www.sgs.com/terms_and_conditions.htm) and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law." Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only