

TEST REPORT NO: 170784

Date: 02 July 2021

**PIERRE FREY SAS
47 RUE DES PETITS CHAMPS
75001 PARIS
FRANCE**

The following sample(s) was/were submitted and identified by/on behalf of the client as:

Retailer	Not Specified
Description of article	F3590 HUASCARAN WOVEN FABRIC
Retailer style number	WHITE
Retailer Standard Number	VOILE
Order No./ Buyer	F3590 HUASCARAN
Quality/Fibre Composition	100% POLYESTER INHERENT FR
Date Sample Received/Test Started:	17 June 2021

Tests	Pass	Fail	Remarks
BS 5867 Part 2 Type B + 12 washes	X		

(Any statement of conformity made in this report unless otherwise stated in the test specification(s) is in line with SGS United Kingdom (Leicester) Decision rule LEI-GEN-PROC-012).

Signature



Stuart Bishop Senior Technician

For and on behalf of
SGS United Kingdom Ltd

All samples are conditioned to ISO 139 where conditioning is required (unless otherwise stated)

This document is issued by the Company under its General Conditions of Service accessible at www.sgs.com/terms_and_conditions.htm and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law." Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only

Customer: **PIERRE FREY SAS** Test Report No: **170784**

Test Results

BS 5867-2: 2008 Fabrics for curtains, drapes and window blinds **Part 2: Flammability requirements – specification Type B**

Description of Test Sample: Huascarán woven fabric

Test Request

As requested, the test specimen supplied has been tested to BS 5867- 2: 2008 type B.

Cleansing Procedure

All fabrics shall be tested before and after the appropriate cleansing or wetting procedure.

Washable Fabric – The test specimen was subject to 12 wash cycles in accordance with BS EN 10528.

Conditioning

The test specimen was conditioned in a standard atmosphere having a temperature of $20 \pm 2^\circ\text{C}$ and a relative humidity of $65 \pm 5\%$ for at least 24 hours.

Specimen Identification

Reputed Fibre Composition – 100% Polyester

Comments on Test Results

The sample supplied meets the requirements of BS 5867-2: 2008 Type B in the as received state.
The sample supplied meets the requirements of BS 5867-2: 2008 Type B in the cleansed state.

Gas Used

Butane

Deviations from test method

None

Flame Application Time

Type B – 15 Seconds

Results

Results may not apply to situations where there is restricted air supply or exposure to large sources of intense heat.

This document is issued by the Company under its General Conditions of Service accessible at www.sgs.com/terms_and_conditions.htm and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law." Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 90 days only

Customer: PIERRE FREY SAS **Test Report No:** 170784

Test Results

Uncertainty

As there is only a definitive pass or fail (any edge reached is a fail) there is no measure of uncertainty.

As Received

Criteria	Length			Width		
	1	2	3	1	2	3
Hole reaching top edge	No	No	No	No	No	No
Hole reaching side edge	No	No	No	No	No	No
Flaming reaching top edge	No	No	No	No	No	No
Flaming reaching side edge	No	No	No	No	No	No
Flaming Debris	No	No	No	No	No	No
Result	Pass	Pass	Pass	Pass	Pass	Pass

After Cleansing Procedure

Criteria	Length			Width		
	1	2	3	1	2	3
Hole reaching top edge	No	No	No	No	No	No
Hole reaching side edge	No	No	No	No	No	No
Flaming reaching top edge	No	No	No	No	No	No
Flaming reaching side edge	No	No	No	No	No	No
Flaming Debris	No	No	No	No	No	No
Result	Pass	Pass	Pass	Pass	Pass	Pass

This document is issued by the Company under its General Conditions of Service accessible at www.sgs.com/terms_and_conditions.htm and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 90 days only

Customer:

PIERRE FREY SAS

Test Report No:

170784

Test Results



End of Report

This document is issued by the Company under its General Conditions of Service accessible at www.sgs.com/terms_and_conditions.htm and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 90 days only