



Date:19 April 2017

TEST REPORT NO:128017

PIERRE FREY SAS
47 RUE DES PETITS CHAMPS
75001 PARIS
FRANCE
FRANCE

The following sample(s) was/were submitted and identified by/on behalf of the client as:

Retailer Not Specified

Description of article Sherlock

Retailer style number 07939

Retailer Standard Number Unknown

Order No./ Buyer 20170403-3

Quality/Fibre Composition 100% Pl

Date Sample(s) Received: 06 April 2017

Test

Schedule 4 Parts I Cigarette Test Schedule 5 Part I Match Test BS EN 1021-2 Ignition Source 1(match) Incl water soak BS5852 Ignition Source 5 (cribs) BS EN 1021-1 Ignition Source 0 (Cigarette) Incl water soak

Remarks

Tests as requested by the customer

Signature



For and on behalf of SGS Leicester Ltd.

All samples are conditioned to ISO 139 where conditioning is required (unless otherwise stated)





Schedule 4 The Cigarette Test Part 1 and Schedule 5 The Match Test Part 1 in accordance with BS 5852: Part 1: 1979

Test Requested

The sample supplied is a Woven fabric and has been tested to the flammability performance requirements of The Furniture and Furnishing (Fire) (Safety) Regulations 1988 S.I No 1324 as amended, Schedule 4 Part 1 The Cigarette Test and Schedule 5 Part 1 The Match Test, using BS 5852: Part 1: 1979.

Fibre Identification

Reputed Fibre Composition: 100% PL

Pre-Treatment

By request of the customer the sample was/ was not subjected to a water soak procedure as described in BS 5651:1978 Clause 4.5 and then line dried.

Conditioning

The sample was conditioned in an indoor ambient condition for at least 72 hours, then for at least 16 hours in an atmosphere having a temperature of 20 ± 5 °C and a relative humidity of 50 ± 20 %.

Comments of Test Results

The sample supplied meets the flammability performance requirements of The Furniture and Furnishings (Fire) (Safety) Regulations 1988 S.I No 1324 as amended Schedule 4 Part 1 The Cigarette Test when tested as stated in the results.

The sample supplied does not meet the flammability performance requirements of The Furniture and Furnishings (Fire) (Safety) Regulations 1988 S.I No 1324 as amended, Schedule 5 Part 1 The Match Test, due to flaming being greater than 120 seconds after the removal of the ignition source.

Results

The following tests results relate only to the ignitability of the combination of materials under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials in use.

The Cigarette Test

Pass Criteria:

Two cigarettes are placed along the junction between the horizontal and vertical test pieces in accordance with Clause 9.2.2. No progressive smouldering or flaming is to be observed within 1 hour of placement of the cigarette (Clause 9.2.4).





The Cigarette Test				
	Cigarette 1	Cigarette 2		
Smouldering Time of the Cigarette	18 min 27 sec	18 min 59 sec		
Clause 9.2.3 Evidence of Progressive Smouldering/ Flaming or Afterglow.	No	No		
Cover Splitting	Yes	Yes		
Clause 9.4 Any Internal Progressive Smouldering during the Final Examination	No	No		
Test Result	Pass	Pass		

The Match Test

Pass Criteria:

A butane flame is applied at the junction between the horizontal and vertical test pieces for a period 20 ± 1 second in accordance with clause 9.3.2. No Flaming or Progressive Smouldering is to be observed after 2 minutes of the removal of the burner tube (Clause 9.3.4).

The Match Test				
		Match 1		
Clause 9.3.4 Evidence of Flaming/ Progressive Smouldering/ Afterglow or Smoking		Yes (Flaming/ Progressive Smouldering/ Afterglow/ Smoking)		
Cover Splitting		Yes		
Clause 9.4 Any Internal Progressive Smouldering during the Final Examination		N/A		
Test Result		Fail		

Smouldering Cigarette test and the match test were carried out over Non-Fire Retardant Polyurethane Foam Density of 20-22 Kg per m³/. The face of the fabric was tested.





EN 1021-1-2:2014

Test Request

The sample supplied is a woven fabric and has been tested to EN 1021-1-2:2014, Smouldering Cigarette and Match Ignition, 0+1.

Fibre Identification

Reputed Fibre Composition: 100% PL

Pre-Treatment

The sample was cleansed using a water-soak procedure at $40\,^{\circ}\text{C}$ ± $1\,^{\circ}\text{C}$ as described in Annex D and line dried.

Conditioning

The sample has been tested after a period of 24 hours of conditioning in a relative humidity of (50±5) % and a temperature of (23±2) °C.

Comments on Test Results

The fabric sample supplied meets the requirements of EN 1021-1-2:2014 Smouldering Cigarette and Match test.

Results

'The following test results relate only to the ignitability if the combination of materials under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard if the materials in use.'

Cigarette Test

Pass criteria:

When two samples are tested no progressive smouldering or flaming is to be observed within 1 hour of placement of the cigarette. If the cigarette fails to smoulder to it complete length, the test is repeated in a new position not less than 50mm from the previous damage. No progressive smouldering is to be present in the final examination.

Cigarette Ignition					
Specimen Number	1	2	3		
Smouldering time of the Cigarette	18 min 41 sec	18 min 55 sec	19 min 26 sec		
Smouldering	NPS	NPS	NPS		
Flaming	N	N	N		
Smoking	N	N	N		
After Glow	N	N	N		
Cover Splitting	Y	Υ	Υ		
Final Examination	Р	Р	Р		





Match Test

Pass Criteria:

Disregard flaming or progressive smouldering which ceases within 120seconds of the removal of the burner tube. Disregard smoking and afterglow which creases within 15minutes of the removal of the burner tube as per British Standards committee CCM/44.No progressive smouldering is to be present in the final examination.

Match Test						
Specimen Number	1	Time	2	Time	3	Time
Smouldering	N	-	N	-	N	-
Flaming	N	-	N	-	N	-
Smoking	Υ	13 sec	Y	14 sec	Υ	17 sec
Afterglow	N	-	N	-	N	-
Cover split		Υ		Υ		Υ
Final Examination		Р		Р		Р

Please note that the fabric sample was tested over Combustion Modified Foam (CMHR) with a density of 35kg per M³.

Key

Y= Yes N=No N/A= Not Applicable
P=Pass F=Fail DNS= Did Not Smoulder

NPS = Non progressive smouldering

PS = Progressive smouldering within 1 hour





BS 5852:2006: Clause 11: Ignition Source 5

Test Request

The sample supplied is a woven fabric and has been tested to BS 5852:2006 Clause 11 using Ignition Source 5

Fibre Identification

Reputed Fibre Composition 100% PL

Pre-Treatment

The sample supplied was water soaked and dried in accordance to BS 5852:2006 Annex E

Conditioning

Before testing the sample was conditioned in an indoor ambient condition for 72 hours and in a standard atmosphere having a temperature of $23^{\circ}C \pm 2^{\circ}C$ and a relative humidity of 50% r.h $\pm 5\%$ for a minimum of 16hours.

Comments on Test Results

The sample supplied meets the requirements of BS 5852:2006 Clause 11, I/5.

Results

"The following test results relate only to the ignitability of combination of upholstery composites (BS 5852:2006 Clause 11) under the particular conditions of the test stated; they are not intended as a means of assessing the full potential fire hazard of the materials or products in use."

Ignition Source 5

Pass Criteria: ~ Disregard flaming which ceases within 10 minutes. Smoke, heat or glowing which ceases within 60 minutes of igniting the crib.

No smouldering is to be present in the final examination.

Specimen Number	1	Time	2	Time
Smoking	Υ	5 min 36 sec	Υ	5 min 59 sec
Smouldering	N	=	N	=
Flaming	Υ	3 min 20 sec	Υ	3 min 31 sec
Afterglow	N	-	Ν	-
Flame front reaches extremities within the test duration (other than the top of	N	N/A	N	N/A
vertical part)				
Cover Split	Υ	N/A	Υ	N/A
Final examination (ignition or Non-Ignition)	Non ignition		Non ignition	

Please note that the fabric sample was tested over combustion-modified foam with a density of 35kg per M³.

Key: Y = Yes N = No N/A = Not Applicable

End of Report