



Date of Issue: 9/26/2025
Report Number: 25-002822
Revision Number:1
Date Order Received: 09/23/2025

For the Account of: Pierre Frey Inc.
1704 Chantilly Dr. NE
Suite 200
Atlanta, GA 30324

Client's Identification: F4076 CHAUSEY

CERTIFICATE OF TESTING

TEST PERFORMED: NFPA 260 Standard Methods of Tests and Classification System for Cigarette Ignition Resistance of Components of Upholstered Furniture – 2024; Fabric Cover Test

TEST RESULTS

Specimen	Char Length (in)	Extinguished in 45 Minutes
1	0.6	Yes
2	0.5	Yes
3	0.5	Yes

NOTES

Test Conditions: 70 ±4°F, 65 ±5% Relative Humidity
Test Environment: 70 ±4°F, 50 ±5% Relative Humidity
Sampling: As Received
Ignition Source: SRM 1196a
Abbreviations: SE = Self-extinguished OBV = Obvious ignition of substrate

ACCEPTANCE CRITERIA

1. If the test specimen has no ignition, or if no individual specimen yields a vertical char of 45 mm (1.75 inches) or greater, the fabric is classified a Class I cover fabric.
2. If the vertical char of any test specimen is greater than 45 mm (1.75 inches), the fabric is classified a Class II cover fabric.
3. If the smoldering extends beyond 45 minutes after placement of the cigarette, the fabric is classified as a Class II cover fabric.
4. If an obvious ignition of the polyurethane substrate occurs on the test assembly, the fabric is classified a Class II cover fabric.

CONCLUSION Based on the above Results and Acceptance Criteria, the item tested is:

Class I
 Class II

CERTIFICATION I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.

Authorized Signature

Date Order Completed: 09/26/2025