



Date: 30 September 2020

TEST REPORT NO: 155769A (Replaces 155769)

Original report dated 10 July 2029

PIERRE FREY SAS 47 RUE DES PETITS CHAMPS 75001 PARIS FRANCE

The following sample(s) was/were submitted and identified by/on behalf of the client as:

Retailer Not Specified

Description of article FABRIC REF F3417 BEATRICE & I6616 OPIO

Retailer style number CREAM
Retailer Standard Number UNKNOWN
Order No./ Buyer 2063613

Quality/Fibre Composition 37% WO 23% ALP 23% MOH 12% COT 5% PA

Date Sample(s) Received: 1 July 2019

Tests	Pass	Fail	Remarks
BS5852 Ignition Source 0 & 1	Х		
BS EN 1021-1/2	Х		

Signature

Lucy Peberdy Technologist

For and on behalf of SGS United Kingdom Ltd

All samples are conditioned to ISO 139 where conditioning is required (unless otherwise stated)
Report 155769A supersedes report 155769 dated 10 July 2019, I6616 OPIO added to the description of the item

This document is issued by the Company under its General Conditions of Service accessible at www.sgs.com/terms_and_conditions.htm and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sgs.com/en/Terms-and-Conditions.aspx. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law." Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only

SGS United Kingdom Ltd





PIERRE FREY SAS **Customer:**

Test Report No:

155769A (Replaces

155769)

Test Results

BS 5852: Part 1: 1979 Methods of test for the ignitability by smokers' materials of upholstered composites for seating.

Test Requested

The test specimen supplied is woven and has been tested using ignition sources 0 and 1 using the following test method BS 5852: Part 1: 1979.

Fibre Identification

Stated Fibre Composition: 37% WOOL 23% ALP 23% MOH 12% COT 5%PA

Conditioning

The materials to be tested and cigarettes were conditioned immediately before the test for 72 hours in an indoor ambient condition and then for at least 16 hours in an atmosphere having a temperature of 20 ± 5°C and a relative humidity of $50 \pm 20 \%$.

Comments of Test Results

The test specimen meets the requirements of clause 9 from BS 5852: Part 1: 1979 using ignition source 0 and 1.

Results

'The following tests results relate only to the ignitability of the combination of materials under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials in use'

This document is issued by the Company under its General Conditions of Service accessible at www.sgs.com/terms_and_conditions.htm and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sgs.com/en/Terms-and-Conditions.aspx. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exenerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.* Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 90 days only

SGS United Kingdom Ltd





Customer: PIERRE FREY SAS Test Report No: 155769A (Replaces 155769)

Test Results

Two cigarettes are placed along the junction between the horizontal and vertical test pieces in accordance with Clause 9.2.2. No progressive smouldering or flaming is to be observed within 1 hour of placement of the cigarette (Clause 9.2.4).

The Cigarette Test			
	Cigarette 1	Cigarette 2	
Clause 9.2.3 Evidence of Progressive Smouldering/ Flaming or Afterglow.	No No		
Cover Splitting	No	No	
Clause 9.4 Any Internal Progressive Smouldering during the Final Examination	No No		
Test Result	Pass	Pass	

A butane flame is applied at the junction between the horizontal and vertical test pieces for a period 20 ± 1 second in accordance with clause 9.3.2. No Flaming or Progressive Smouldering is to be observed after 2 minutes of the removal of the burner tube (Clause 9.3.4).

The Match Test			
	Match 1	Match 2	
Clause 9.3.4 Evidence of Flaming/ Progressive Smouldering/ Afterglow or Smoking	No	No	
Cover Splitting	No	No	
Clause 9.4 Any Internal Progressive Smouldering during the Final Examination	No	No	
Test Result	Pass	Pass	

Smouldering Cigarette test and the match test were carried out over Non-Fire Retardant Polyurethane Foam Density of 20-22 Kg per m³.

The face of the fabric was tested.

This document is issued by the Company under its General Conditions of Service accessible at www.sgs.com/terms_and_conditions.htm and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sgs.com/en/Terms-and-Conditions.aspx. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law." Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 90 days only





Customer:

PIERRE FREY SAS

Test Report No:

155769A (Replaces

155769)

Test Results

BS EN 1021 -1 & 2:2014

Assessment of the ignitability of upholstered furniture Part 1 – Ignition source smouldering cigarette / Part 2 – Ignition source match flame

Description of Test Sample: Cream fabric

Test Requested

The test specimen has been tested to BS EN 1021 – 1 & 2: 2014 Smouldering cigarette and match flame.

Pre - Treatment

The customer has stated that the supplied test specimen has not been chemically treated so therefore no water soaking procedure has been performed.

Conditioning

All materials to be tested and the cigarettes have been conditioned for at least 24 hours immediately before the tests in an atmosphere $23 \pm 2^{\circ}$ C and $50 \pm 5\%$ r.h.

Comments on Test Results

The test specimen meets the requirements of BS EN 1021-1 & 2: 2014 where the result for both tests has been stated as non-ignition.

Test Results

'The test results relate only to the ignitability of the combination of materials under particular conditions of test; they are not intended as a means of assessing the full fire hazard of the materials in use.'

This document is issued by the Company under its General Conditions of Service accessible at www.sgs.com/terms_and_conditions.htm and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sgs.com/en/Terms-and-Conditions.aspx. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exenerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.* Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 90 days only

SGS United Kingdom Ltd





Customer: PIERRE FREY SAS Test Report No: 155769A (Replaces 155769)

Test Results

Ignition source Smouldering Cigarette

	Criteria of ignition	Cigarette 1 Criteria Observed	Cigarette 2 Criteria Observed
sive ring n	Clause 3.1a	No	No
	Clause 3.1b	No	No
ogressi noulderi ignition	Clause 3.1c	No	No
Progressive smouldering ignition	Clause 3.1d	No	No
	Clause 3.1e	No	No
Flaming Ignition	Occurrence of flames	No	No
	Ignition occurring	Non – Ignition	Non – Ignition

Ignition source Match Flame

	Criteria of Ignition	Match Flame 1 Criteria Observed	Match Flame 2 Criteria Observed
Progressive smouldering ignition	Clause 3.1a	No	No
	Clause 3.1b	No	No
	Clause 3.1c	No	No
	Clause 3.1d	No	No
	Clause 3.1e	No	No
Flaming Ignition	Clause 3.2a	No	No
	Clause 3.2b	No	No
	Clause 3.2c	No	No
	Clause 3.2d	No	No
	Ignition occurring	Non – Ignition	Non – Ignition

The test specimen was tested over Combustion modified foam (CMHR) with a density of 35kg/m³.

This document is issued by the Company under its General Conditions of Service accessible at www.sgs.com/terms_and_conditions.htm and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sgs.com/en/Terms-and-Conditions.aspx. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law." Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 90 days only

SGS United Kingdom Ltd





Customer: PIERRE FREY SAS Test Report No: 155769A (Replaces 155769)

Test Results

Smouldering criteria of Ignition

- Clause 3.1a Test assembly displays escalating combustion behaviour so that it is unsafe to continue
- Clause 3.1b Test assembly that smoulders until it is largely consumed
- Clause 3.1c Test assembly that smoulders to the extremities within the test duration
- Clause 3.1d Test assembly that smoulders after one hour from application of the ignition source
- Clause 3.1e Test assembly on final examination shows evidence of progressive smouldering

Flaming Ignition

- Clause 3.2a Test assembly displays escalating combustion behaviour so that it is unsafe to continue
- Clause 3.2b Test assembly burns until it is essentially consumed
- Clause 3.2c Flame reaches the lower margin, either side or passed through the full thickness
- Clause 3.2d Flaming continues for more than 120 seconds after removal of burner tube

End of Report



This document is issued by the Company under its General Conditions of Service accessible at www.sgs.com/terms_and_conditions.htm and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at http://www.sgs.com/en/Terms-and-Conditions.aspx. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law." Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 90 days only

SGS United Kingdom Ltd