

For the Account of: Pierre Frey Inc.
1704 Chantilly Dr. NE
Suite 200
Atlanta, GA 30324

Client's Identification: F3830 Alassio and F3831 Rimini

CERTIFICATE OF TESTING

TEST PERFORMED: NFPA 260 Standard Methods of Tests and Classification System for Cigarette Ignition Resistance of Components of Upholstered Furniture – 2013; Fabric Cover Test and UFAC Fabric Classification Test Method – 1990; Standard Test Methods for Cigarette Ignition Resistance of Components of Upholstered Furniture ASTM E 1353-16 – Cover Fabric Test

TEST RESULTS

Specimen	Char Length (in)
1	0.5
2	0.4
3	0.5

NOTES

Test Conditions: 70 ±4°F, 65 ±5% Relative Humidity

ACCEPTANCE CRITERIA

1. If the test specimen has no ignition, or if no individual specimen yields a vertical char of 45 mm (1.75 in; ASTM states 1.8 in.) or less, the fabric is classified a Class I cover fabric.
2. If the vertical char of the test specimen greater than 45 mm (1.75 in.; ASTM states 1.8 in), the fabric is classified a Class II cover fabric.
3. If an obvious ignition of the polyurethane substrate occurs on the test assembly, the fabric is classified a Class II cover fabric.

CONCLUSION Based on the above Results and Acceptance Criteria, the item tested is:

- Class I
 Class II

CERTIFICATION I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.



Authorized Signature

Date Order Completed: 11/29/2023