

TEST REPORT NO: 215169

Date: 02 September 2025

PIERRE FREY SAS
47 RUE DES PETITS CHAMPS
75001 PARIS
FRANCE

The following sample(s) was/were submitted and identified by/on behalf of the client as:

Retailer	Not Specified
Description of article	I6661 PITTI - FABRIC
Retailer style number	BROWN/WASHED BLUE
Retailer Standard Number	UNKNOWN
Order No./ Buyer	ADELE MOSA
Quality/Fibre Composition	UNKNOWN
Date Sample Received/Test Started:	20 August 2025

Tests	Pass	Fail	Remarks
Schedule 4 Parts I Cigarette Test	X		
Schedule 5 Part I Match Test		X	

(Please note our uncertainty of measurement has been taken into account when the above results were pass/failed)
Binary Statement with Guard Band Rule. Here the lab reduces the tolerance specified in the test standard by the test uncertainty. So if the measured result now falls within the revised tolerance then the result is deemed a PASS. However, if the result falls outside the revised tolerance, then the result is deemed a FAIL with the risk of an incorrect result or statement of conformity being reported is <2.5%.

Signature



Lucy Peberdy Technologist

For and on behalf of
SGS United Kingdom Ltd

All samples are conditioned to ISO 139 where conditioning is required (unless otherwise stated)

This document is issued by the Company under its General Conditions of Service accessible at www.sgs.com/terms_and_conditions.htm and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only

Customer: PIERRE FREY SAS Test Report No: 215169

Test Results

BS 5852: Part 1: 1979

Methods of test for the ignitability by smokers' materials of upholstered composites for seating.

Test Requested

The test specimen supplied is Brown / Washed Blue and has been tested using ignition sources 0 and 1 using the following test method BS 5852: Part 1: 1979.

Fibre Identification

Stated Fibre Composition: Unknown

Conditioning

The materials to be tested and cigarettes were conditioned immediately before the test for 72 hours in an indoor ambient condition and then for at least 16 hours in an atmosphere having a temperature of $20 \pm 5^{\circ}\text{C}$ and a relative humidity of $50 \pm 20\%$.

Comments of Test Results

The test specimen meets the requirements of clause 9 from BS 5852: Part 1: 1979 using ignition source 0.

The test specimen does not meet the requirements of clause 9 from BS 5852: Part 1: 1979 using ignition source 1, due to flaming ignition.

Results

'The following tests results relate only to the ignitability of the combination of materials under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials in use'

This document is issued by the Company under its General Conditions of Service accessible at www.sgs.com/terms_and_conditions.htm and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law." Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only

Customer: PIERRE FREY SAS **Test Report No:** 215169

Test Results

Two cigarettes are placed along the junction between the horizontal and vertical test pieces in accordance with Clause 9.2.2. No progressive smouldering or flaming is to be observed within 1 hour of placement of the cigarette (Clause 9.2.4).

The Cigarette Test		
	Cigarette 1	Cigarette 2
Clause 9.2.3 Evidence of Progressive Smouldering/ Flaming or Afterglow.	No	No
Cover Splitting	Yes	Yes
Clause 9.4 Any Internal Progressive Smouldering during the Final Examination	No	No
Test Result	Pass	Pass

A butane flame is applied at the junction between the horizontal and vertical test pieces for a period 20 ± 1 second in accordance with clause 9.3.2. No Flaming or Progressive Smouldering is to be observed after 2 minutes of the removal of the burner tube (Clause 9.3.4).

The Match Test	
	Match 1
Clause 9.3.4 Evidence of Flaming/ Progressive Smouldering/ Afterglow or Smoking	Yes Flaming
Cover Splitting	Yes
Clause 9.4 Any Internal Progressive Smouldering during the Final Examination	N/A
Test Result	Fail

Smouldering Cigarette test and the match test were carried out over Non-Fire Retardant Polyurethane Foam Density of 20-22 Kg per m³. The face of the fabric was tested.

The test specimen was extinguished due to flaming being greater than 120 seconds.

Measurement of uncertainty

Ignition source 0: +0sec/-60sec progressive smouldering

Ignition source 1: +0sec/-60sec smouldering +0sec/-2sec flaming

This document is issued by the Company under its General Conditions of Service accessible at www.sgs.com/terms_and_conditions.htm and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only

Customer:

PIERRE FREY SAS

Test Report No:

215169

Test Results



End of Report

This document is issued by the Company under its General Conditions of Service accessible at www.sgs.com/terms_and_conditions.htm and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law." Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only