



Report Number: 75947 Date: 11-2-2015

CERTIFICATE OF TESTING

For the Account Of: Pierre Frey, Inc.

1692 Chantilly Drive NE

Suite C

Atlanta, GA 30324

Contact: Caitlin Whitley

Client's Identification: Gaspard

TEST PERFORMED California Technical Bulletin 117: June 2013 – Requirements, Test Procedure and Apparatus for

Testing the Smolder Resistance of Materials Used in Upholstered Furniture – Cover Fabric Test

TEST RESULTS

| Specimen | Char Length (in) | Extinguished in 45 minutes? (Y/N) |
|----------|---------------------|---|
| 1 | 0.6 | Υ |
| 2 | 0.6 | Υ |
| 3 | 0.6 | Υ |

0.6 **NOTES**

Test Conditions: 70 \pm 5°F, 50 \pm 5% Relative Humidity

ACCEPTANCE CRITERIA

A material is considered to pass or fail based on the following criteria:

- 1. A single mock-up test specimen fails to meet the requirements of this test procedure if any of the following criteria occurs:
 - a. The mock-up test specimen continues to smolder after the 45 minute test duration
 - b. A vertical char length of more than 1.8 inches (45mm) develops on the cover fabric
 - c. The mock-up test specimen transitions to open flaming
- 2. The cover fabric passes the test if three initial mock-up specimens pass the test, i.e. the cigarettes burn their full length and are no longer smoldering
- 3. If more than one initial specimen fails, the cover fabric fails the test
- 4. If any one of the three initial specimens fails, repeat the test on additional three specimens
- 5. If all three additional specimens pass the test, the cover fabric passes the test. If any one of the additional three specimens fails, the cover fabric fails the test

| CONCLUSION | Based on the above Results and Acceptance Criteria, the item tested is: |
|------------|---|
| | □ Pass |
| | ☐ Fail |

CERTIFICATION I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.

Authorized Signature N