

## Centro Tessile Serico Sostenibile Srl

via Castelnuovo, 3 - 22100 Como Italia

Pho +39 031 3312111/120 Fax: +39 0313312149 Amministrazione/Contabilità +39 031 3312102-154

P. IVA - C.F. 03900470133

Capitale sociale euro 600000,00 iv

mailbox@textilecomo.com www.textilecomo.com

Test Report No.: **2500795-001** 

2500795

Date Test Report 14-feb-25

Arrival date sample 12-feb-25

Start date test 12-feb-25

End date test 14-feb-25

References:

[C] Item:

Acceptance:

Sampling Mode: Sampling by Customer

[C] Declared Composition: 70% Wool - 22% Cotton - 8% Polyester

[C] End use: furnishing
[C] Typology: velvet

Return: sample enclosed

## **Test Results**

Customer Code 08798

**PIERRE FREY SAS** 

75001 Paris Francia

47 Rue Des Petits Champs

Adeline Jelago

Dear:

C.a.

Phone:

Test Method U.M. Result

F4065 GABRIEL

UNI 9176: 1998 - Metodo D

15196 PREPARATION OF MATERIALS FOR

BURNING BEHAVIOUR TESTS: BRUSHING IN

DETERGENT SOLUTION

 Start date test
 12/02/2025

 End date test
 13/02/2025

Instrument: Brusher - ATS FAAR

Procedure:

Sample was submitted to brushing (200 cycles) in an aqueous detergent solution (2% w/w) and rinsed with stream water.

After the conditioning, the sample was submitted to fire reaction test, as following described.

Deviations from the method None

15036 REACTION TO FIRE OF FURNITURE BY

APPLYING A SMALL FLAME

ITURE BY UNI 9175:1987 + A1:1994

Start date test 13/02/2025
End date test 14/02/2025
Instrument: Small Test Rig and burner

Pretreatment carried out sample was submitted to brushing, as above described

Upholstery filling test result (flame 20 s)

NOTE:

In absence of effective upholstery filling, the test has been carried out using a FLAME RETARDANT POLYURETHANE FOAM with a density of 35 kg/m³ (HR35D) as filling of the upholstered seating.

This foam meets the test requirements for the upholstery filling (test on upholstery filling - without outer cover material - 20 s of flame time application).

The test result could be different using another type of filling material.

Upholstery filling test result (flame 20 s)

- POSITIVE

Upholstery test result (flame 80 s)

- POSITIVE

Upholstery test result (flame 140 s)

- POSITIVE

TEST RESULT

SAMPLE MEET THE CLASS 1.IM

Deviations from the method

The Results contained in this Report refer only to the sample as received and to the objects tested and do not imply an approval of the tested product by the Laboratory of the Centro Tessile Serico Sostenibile Srl. Unless otherwise specified, the side examined / straight of use is indicated by the Customer: this information can influence the results of the tests and therefore the Test Laboratory declines all responsibility.

This Report may not be reproduced in part, unless written permission of Centro Tessile Serico Sostenibile Srl Laboratory.

[C] = Information provided by the Customer, of which the Centro Tessile Serico Sostenibile Srl Laboratory declines all responsibility.



## Centro Tessile Serico Sostenibile Srl

via Castelnuovo, 3 - 22100 Como Italia Pho +39 031 3312111/120 Fax: +39 0313312149 Amministrazione/Contabilità +39 031 3312102-154

P. IVA - C.F. 03900470133

Capitale sociale euro 600000,00 iv mailbox@textilecomo.com

Test Report No.: 2500795-001

Test	Method	U.M.	Result
Annex n.			1F
Details of the test results related to	each specimen can be seen in the annex of this test report.		

The Laboratory Manager

Fausto Albonico

**END OF REPORT**