



For the Account of Pierre Frey Inc.
1704 Chantilly Dr. NE
Suite 200
Atlanta, GA 30324

Client's Identification I6615 CAPRI II

CERTIFICATE OF TESTING

TEST PERFORMED NFPA 260 Standard Methods of Tests and Classification System for Cigarette Ignition Resistance of Components of Upholstered Furniture – 2024; Fabric Cover Test

TEST RESULTS

Specimen	Char Length (in)	Extinguished in 45 Minutes
1	0.6	Yes
2	0.6	Yes
3	0.5	Yes

NOTES

Test Conditions 70 ±4°F, 65 ±5% Relative Humidity
Test Environment 70 ±4°F, 50 ±5% Relative Humidity
Sampling As Received
Ignition Source SRM 1196a

ACCEPTANCE CRITERIA

1. If the test specimen has no ignition, or if no individual specimen yields a vertical char of 45 mm (1.75 inches) or greater, the fabric is classified a Class I cover fabric.
2. If the vertical char of any test specimen is greater than 45 mm (1.75 inches), the fabric is classified a Class II cover fabric.
3. If the smoldering extends beyond 45 minutes after placement of the cigarette, the fabric is classified as a Class II cover fabric.
4. If an obvious ignition of the polyurethane substrate occurs on the test assembly, the fabric is classified a Class II cover fabric.

CONCLUSION Based on the above Results and Acceptance Criteria, the item tested is:

- Class I
 Class II

CERTIFICATION I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.

Authorized Signature

Date Order Completed: 04/03/2026